



Elektron[®] WE43B

Elektron WE43B is a high strength magnesium based casting alloy developed and patented by Luxfer MEL Technologies for use at temperatures up to 300°C. This alloy system maintains its good mechanical properties at elevated temperatures, without the use of either silver or thorium. The alloy is stable for long term exposure up to 250°C. Elektron WE43B has excellent corrosion resistance characteristics.

Applications

The excellent retention of properties at elevated temperatures will be of interest to designers of aeroengines and other power systems, helicopter transmissions, missiles, racing and high performance cars.

Specifications

UNS No. M18430
ASTM B80
AMS 4427
MAM 4427
AECMA MG-C96002
ISO 16220: MC95310

Chemical composition

Yttrium	3.7–4.3%
Rare earths	2.4–4.4%
Zirconium	0.4% min
Magnesium	Balance

Heat treatment

The alloy develops its optimum properties in the fully heat treated condition ie:
Solution heat treat for 8 hours at 525°C,
Air cool, hot water or polymer quench,
Age for 16 hours at 250°C, Air cool.

Physical properties

Specific gravity	1.84
Coefficient of thermal expansion	26.7 x10 ⁻⁶ K ⁻¹
Thermal conductivity	51 Wm ⁻¹ K ⁻¹
Specific heat	966 Jkg ⁻¹ K ⁻¹
Electrical resistivity	148 nΩm
Modulus of elasticity	45 x 103 MPa
Poissons ratio	0.27
Melting range	540–640°C
Damping index	0.09
Vickers hardness	85–105

Design data

Minimum specification tensile properties:	
0.2% proof stress	172 MPa
Tensile strength	220 MPa
Elongation	2%

Other properties

Castability

Fine grained and pressure tight with good casting characteristics.

Pattern makers shrinkage factor

1.5%

Weldability

Fully weldable by the tungsten arc inert gas (TIG) process, using filler rods of the parent alloy composition.

Machining

Elektron WE43B castings, like all magnesium alloy castings, machine faster than any other metal. Providing the geometry of the part allows, the limiting factor is the power and speed of the machine rather than the quality of the tool material. The power required per cubic centimetre of metal removed varies from 9 to 14 watts per minute depending on the operation.

Table 1. Cut up properties on samples taken from actual castings.

Temperature	Number of tests		0.2% proof stress (MPa)	Tensile strength (MPa)	Elongation (%)
20°C	215	Minimum	149	200	2
		Average	178	250	7
		Maximum	215	293	17
250°C	56	Minimum	134	187	2
		Average	155	211	18
		Maximum	193	235	36

Discover more at
www.luxfermeltechnologies.com



[†] The information contained within is meant as a guideline only

Copyright © Luxfer MEL Technologies 2018. The information provided within this document is aimed to assist manufacturers and other interested parties in the use of Luxfer MEL Technologies products. Luxfer MEL Technologies accepts no liability in whole or in part from use and interpretation of the data herein. All information is given in good faith but without warranty. Freedom from patent rights must not be assumed. Health and Safety information is available for all Luxfer MEL Technologies products. **DS-1021-11118**



Certificate No. FM12677

Luxfer MEL Technologies
 Elektron Technology Centre
 Lumns Lane, Manchester, M27 8LN, UK
 T +44 (0) 161 911 1000

Luxfer MEL Technologies
 500 Barbertown Point Breeze Road
 Flemington, NJ 08822, USA
 T +1 908 782 5800

Luxfer MEL Technologies
 4601 Westown Parkway Suite 130
 West Des Moines, IA 50266
 T +1 515 421 4100